

Structural carbon steel with max. operating temperature $\leq 80^{\circ}\text{C}$ in internal and fully dry and ventilated areas

System no.	Surface preparation	Coating system	DFT μm
8A-1	Sa 2½	Penguard Universal	<u>150</u> 150
8A-2	Sa 2½	Jotamastic 90 WG	<u>150</u> 150
8B-1	Sa 2½	Barrier Plus Penguard Tie Coat 100	60 <u>25</u> 85